

A3B1
9. (Amended) A structure according to any one of claims 1, 2 and 3, wherein said thin metal film has a thickness of 0.03-1.0 μ m.

A4 sum B1
20. (Amended) A method for manufacturing a surface structure formed on an aluminum wheel for an automobile, said method comprising:
(a) coating a resin film on said aluminum wheel; and
(b) forming a thin metal film on said resin film, wherein said thin metal film is made from a titanium-aluminum alloy containing 20-50% by weight of titanium and 80-50% by weight of aluminum formed by any one of cathode arc-type ion plating and sputtering using a sintered target containing titanium and aluminum.

B1
A5
22. (Amended) A method for manufacturing a surface structure formed on an aluminum wheel for an automobile, said method comprising:
(a) coating a resin film on said aluminum wheel;
(b) forming a thin metal film on said resin film, wherein said thin metal film is made from a titanium-aluminum alloy containing 20-50% by weight of titanium and 80-50% by weight of aluminum formed by any one of cathode arc-type ion plating and sputtering using a sintered target containing titanium and aluminum; and
(c') coating a clear colored protective film on said thin metal film.

A6 B1
30. (Amended) A method according to any one of claims 20, 21 and 22, wherein said thin metal film has a thickness of 0.03-1.0 μ m.

See the attached Appendix for the changes made to effect the above claims.